

Manufacture Spec.

Description: Bi-colour heavy medium weight flock lined natural rubber gloves

- Features & Benefits:
- * Anatomically shaped for comfort
 - * Anti-slip pattern for good grip in wet and dry conditions
 - * Natural rubber
 - * Palm strengthened with extra dip
 - * Pinked or straight cuff
 - * Pure cotton lining to absorb perspiration

Applications: Agriculture, Food Industry, Laboratories, Facility maintenance



Elastomer: Natural rubber

Thickness: 0.60 +/- 0.06 mm

Lining: Flocklined

Former: Honeycomb CIH

Exterior: Chlorinated

Cuff Types: Pinked or Straight

Treatments: Chlorinated

Colours: Blue on Yellow B4/Y1, Green on Yellow G11/Y1, Green on Yellow (G10/Y1)

AQL - Critical: 1.5

Major: 4.0

CE Certification: Conforms to PPE Regulation EU 2016/425 to (Complex Design) Personal Protective Equipment after assessment against standards EN ISO 21420:2020, EN ISO 374-1:2016+A1:2018, EN ISO 374-5:2016 and EN 388:2016+A1:2018

Conforms to: ASTM D4679 of 2021

| Physical Dimensions: | Size | Palm | Wrist | Cuff | Length |
|----------------------|-------|-------------------------------|-------|---------------|--------|
| | XS | 182 | 170 | 222 | 300 |
| | 6-6.5 | 198 | 183 | 248 | 300 |
| | 7-7.5 | 208 | 190 | 251 | 300 |
| | 8-8.5 | 215 | 202 | 268 | 300 |
| | 9-9.5 | 235 | 226 | 280 | 300 |
| | XL | 250 | 237 | 293 | 310 |
| | | Circumference in mm, +/- 5 mm | | Tol. +/- 5 mm | |

Permanent Set Value 10 (%):
Shelf Life 3 Years

Moisture Content 0.6 (%):

Extractable Protein Content 50 (µg/g):

Physical Properties: Tensile strength: 18.0 MPa (min)
Elongation at break: 700% (min)

Modulus at 500% elongation: 5.5 MPa (max)
Load at break: 40.0 N (min)

Protection against Chemical hazards

Performance

Degradation %

EN ISO 374-1/TYPE A



| | | |
|------------------------------|---------|-------|
| * Methanol (A) | Level 2 | 9.4 |
| * Sodium hydroxide 40% (K) | Level 6 | -2.4 |
| * Sulphuric acid 96% (L) | Level 3 | 36 |
| * Nitric acid 65% (M) | Level 5 | 2.1 |
| * Acetic acid 99% (N) | Level 2 | 8.5 |
| * Ammonium hydroxide 25% (O) | Level 1 | -16.8 |
| * Hydrogen peroxide 30% (P) | Level 6 | 5.7 |

Note: Printed copies are valid only on the date printed

Printed Date: 26-Feb-2024

Revision:8

Published Date: 21-Feb-2024

DPL
Handling you with care

No: 400, Deans Road, Colombo 10, Sri Lanka

Phone: +94-0122-683-964

Fax: +94-0122-699-018

E-Mail: postmast@dplgroup.com

| |
|--------------------------|
| Manufacture Spec. |
|--------------------------|

| | | |
|-----------------------------|---------|---|
| * Formaldehyde 37% (T) | Level 6 | 2 |
| * Hydrofluoric acid 40% (S) | Level 6 | X |

| | |
|--|--------------------|
| Protection against Mechanical hazards | Performance |
|--|--------------------|

EN 388



| | |
|------------------------|---------|
| * Abrasion resistance | Level 1 |
| * Blade cut resistance | Level 0 |
| * Tear resistance | Level 1 |
| * Puncture resistance | Level 0 |
| * TDM cut resistance | X |

| | |
|--|--------------------|
| Protection against Micro-organisms risk | Performance |
|--|--------------------|

EN ISO 374-5

| | |
|---|------|
| * Protection against bacteria and fungi | Pass |
| * Protection against viruses | n/a |